

Katotlar	Kimyasal kořutluk % (m/m)									
	Element	CU	Pb	S	Se	Te	Bi	Sb	As	Fe
GA	min.	99.99	-	-	-	-	-	-	-	-
	maks.	-	0.0005	0.0015	0.0002	0.0001	0.0002	0.0004	0.0005	0.001
10 ppm Pb/20 ppm S	min.	99.99	-	-	-	-	-	-	-	-
	maks.	-	0.001	0.002	0.0002	0.0001	0.0002	0.0004	0.0005	0.001
20 ppm Pb/ 40 ppm S	min.	99.99	-	-	-	-	-	-	-	-
	maks.	-	0.002	0.004	0.0002	0.0001	0.0002	0.0004	0.0005	0.001
50 ppm Pb / 50 ppm S	min.	99.98	-	-	-	-	-	-	-	-
	maks.	-	0.005	0.005	0.0002	0.0001	0.0002	0.0004	0.0005	0.001

| |